

Product Data Sheet

RustPro C2

Description and Applications

Saheli RustPro C2 is water displacing type rust preventive and leaves an oily greasy protective film. It is specifically designed to provide medium-term protection of spare parts, components and machined surfaces made of ferrous and non-ferrous metals including aluminum, copper and their alloys with improved coverage.

Saheli RustPro C2 is blended from selected rust prevention components and solvent to provide excellent dewatering properties, effective protective film and fast drying capability.

Features and Benefits

- Facilitates rapid removal of water or coolant from metal surfaces.
- Effective fingerprint corrosion suppressant thus making the film resistant to handling.
- Forms effective protective film against aggressive atmospheres.
- Excellent spreading allowing them to be applied either by dipping or by spraying.
- Rapid drying assists in increasing process speed.

Applications

- **Saheli RustPro C2** is recommended for medium-term protection of precision metal components made of ferrous and non-ferrous metals including aluminum, copper and their alloys after machining, extrusion, galvanizing or degreasing/ washing processes.

Usage

- **Saheli RustPro C1** is best applied by dipping but if such facilities are not available it can also be sprayed. However, all precautions applicable to solvent-based products should be observed.
- Brushing of the fluid can also be used but extra care must be taken to ensure that brush fibers or extraneous dirt/ particulates are not inadvertently introduced as they have negative impact on anti-corrosion performance.
- The protective films can be removed by wiping off with rags/waste soaked in kerosene/mineral turpentine or by alkaline degreasants or solvent degreasing methods.

NOTE: Saheli RustPro C2 is compatible with normal steel components and pipework prevalent in the construction of application systems. Care should be exercised with selection and use of seals and paints in contact with this product.

Specifications

ISO 6743-8 (1987): ISO-L-REE category

Product Data Sheet

RustPro C2

Test Parameters	Test Method	Typical Results
Density @ 15°C gm/cm ³	ASTM D1298	0.802
Viscosity @ 20°C (cSt)	ASTM D 445	2.8
Pour Point °C	ASTM D 97	-54
Flash Point (PMCC) °C	ASTM D 93	42
Coverage (m ² /l)		60
Film Thickness, microns		4
Salt Spray Test, hours to fail	ASTM B 117	100+
Humidity Cabinet, days to fail	ASTM D 1748	120+
Indoor Protection, months		9
Outdoor Protection, months		3

The information contained in this data sheet are indicative and correspond to the date of publication of this document. The above data are based on laboratory tests. It is the reader's interest to ensure whether the most recent version of the data sheet. A safety data sheet is available on request by our sales consultant. For more information, please contact the sales department.

Saheli Energy Solutions P.O.Box : 500102 Fax : +971 44301710 Dubai, UAE - info@saheli-lubes.com - www.saheli-lubes.com